

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-072238

(43)Date of publication of application : 17.03.1998

(51)Int.Cl.

C03C 3/12

C03C 21/00

(21)Application number : 09-124873

(71)Applicant : CARL ZEISS:FA

(22)Date of filing : 28.04.1997

(72)Inventor : SPEIT BURKHARD DR

(30)Priority

Priority number : 96 19616633 Priority date : 26.04.1996 Priority country : DE

(54) CHEMICALLY TEMPERABLE ALUMINOSILICATE GLASS AND ITS USE

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain chemically temperable aluminosilicate glass contg. a small number of bubbles of small size.

SOLUTION: This glass has a compsn. consisting of, by mol, 63.0-67.5% SiO₂, 9.5-12.0% Al₂O₃, 8.5-15.5% Na₂O, 2.5-4.0% K₂O 3.0-9.0% MgO, 0-2.5% CaO+SrO+ BaO+ZnO, 0.5-1.5% TiO₂, 0.02-0.5% CeO₂, 0.02-0.35% As₂O₃, 0-1.0% SnO₂ and 0.05-2.6% F₂ and satisfies $5.3 \leq \text{SiO}_2/\text{Al}_2\text{O}_3 \leq 6.85$, $3.0 \leq \text{Na}_2\text{O}/\text{K}_2\text{O} \leq 5.6$, $2.8 \leq \text{Al}_2\text{O}_3/\text{K}_2\text{O} \leq 3.6$ and $7.8 \leq \text{Al}_2\text{O}_3/(\text{TiO}_2 + \text{CeO}_2) \leq 18.5$. In the case where As is not contained, 0.02-1.0% SnO₂ and >0.5 to 2.6% F₂ are contained.